



ข้อมูลทางวิชาการ

สีน้ำอะครีลิคเจบีพีสมาร์ทโค้ท ชนิดกึ่งเงา

คำอธิบาย

ด้วยเทคโนโลยี Ultra Protection ทำให้ฟิล์มสีทนทานทุกสภาวะ 2 เท่า เสริมความแกร่งให้ฟิล์มสี ปกป้องโครงสร้างบ้านของคุณ ให้ทนทานในทุกสภาวะแวดล้อม ด้วยอนุภาพไมโครสเฟียร์เซรามิกที่ทำหน้าที่เป็นฉนวนสะท้อนความร้อน ช่วยลดการถ่ายเทความร้อนเข้าสู่ตัวอาคารได้เป็นอย่างดี เพิ่มประสิทธิภาพความทนทานต่อการขีดข่วนทำความสะอาด ด้วยการเรียงตัวของอะครีลิคในรูปแบบ Compact Layer ฟิล์มสีติดแน่น ทนทาน สวยงามยาวนานกว่าสีทั่วไป ช่วยลดการสะสมของสิ่งสกปรก เชื้อรา และตะไคร่น้ำ ปราศจากสารตะกั่วและปรอท ปลอดภัยต่อผู้ใช้และผู้อยู่อาศัย เหมาะสำหรับทาบนพื้นผิวปูนฉาบ คอนกรีต อิฐ ยิปซัม และกระเบื้องแผ่นเรียบ

การใช้

พื้นผิวปูนฉาบ คอนกรีต อิฐ ยิปซัม และกระเบื้องแผ่นเรียบ

ลักษณะสี

กึ่งเงา

เฉดสี

สามารถเลือกได้จากเฉดสีในแคตตาล็อก หรือ เครื่องผสมสีอัตโนมัติ

คุณสมบัติทางกายภาพ

ชนิดของสารยึดเกาะ	: 100% อะครีลิคลาเท็กซ์
ชนิดของผงสี	: โทเทเนียมไดออกไซด์ และเม็ดสีทนแสงตามเฉดที่ต้องการ
ชนิดของตัวทำละลาย	: น้ำสะอาด
เนื้อสีโดยน้ำหนัก	: 33 - 35 % (Lab:อ้างอิงสีขาว เบอร์ G-200)
เนื้อสีโดยปริมาตร	: 23 - 25 % (Lab:อ้างอิงสีขาว เบอร์ G-200)
ความหนาฟิล์มเมื่อแห้ง	: 35 - 40 ไมโครเมตร
ความหนาฟิล์มเมื่อเปียก	: 150 - 160 ไมโครเมตร
การปกคลุมพื้นที่ ทางทฤษฎี	: 32 - 37 ตารางเมตร / แกลลอน / เทียว
การปกคลุมพื้นที่ ทางปฏิบัติ*	: 27 - 31 ตารางเมตร / แกลลอน / เทียว
	: *(สูญเสีย 15% โดยประมาณ) ที่ความแห้งที่ 30 องศาเซลเซียส
ระยะเวลาแห้งสัมผัส	: ภายใน 30 นาที
ระยะเวลาแห้งทาทับ	: ภายหลัง 2 ชั่วโมง
ระยะเวลาแห้งสมบูรณ์	: ภายหลัง 24 ชั่วโมง

มาตรฐาน

มอก. 2321-2549 (มาตรฐานอุตสาหกรรม สีอีมีลชั้นเกรดทนสภาวะอากาศ)
ฉลากเขียว ประเทศไทย

การบรรจุ

สีเบอร์	: 1 แกลลอน (3.5 ลิตร), 5 แกลลอน (17.5 ลิตร)
สีเบส	: 1 แกลลอน (3.5 ลิตร), 2.5 แกลลอน (8.75 ลิตร)

สถานะการเก็บรักษา

จัดเก็บสินค้าในที่แห้งมีอากาศถ่ายเทดี ปิดฝาให้สนิท ไม่ควรเก็บที่ร้อนและไม่ให้ถูกแสงแดดโดยตรง

อายุผลิตภัณฑ์

3 ปี ที่อุณหภูมิ 30 - 35 องศาเซลเซียส

สถานะการใช้งาน

ที่อุณหภูมิบรรยากาศและพื้นผิว 13 - 38 องศาเซลเซียส ความชื้นสัมพัทธ์ < 85%



ข้อมูลทางวิชาการ

สีน้ำอะครีลิคเจบีพีสมาร์ทโค้ท ชนิดกึ่งเงา

การเตรียมพื้นผิว

พื้นผิวปูนใหม่

ทิ้งให้ผนังปูนแห้งสนิทอย่างน้อย 1 เดือน หรือเช็คค่าความชื้นที่ผิวมีค่าไม่เกิน 14% ทำความสะอาดพื้นผิวให้ปราศจากสิ่งสกปรก ฝุ่น คราบไข ด้วยผ้า แปรง (ห้ามใช้แปรงลวดขัดเนื่องจากจะทำให้เกิดสนิม) น้ำสะอาด หรือสารละลายผงซักฟอกทิ้งให้แห้ง

พื้นผิวปูนเก่า

ขัดล้างสีเดิมที่เสื่อมสภาพออกให้หมด(ห้ามใช้แปรงลวด) สำหรับบริเวณที่มี เชื้อราหรือตะไคร่น้ำ ควรขัดทำความสะอาด ด้วย JBP MouldWash ทิ้งไว้ให้ แห้ง 3 ชั่วโมง โดยไม่ต้องล้างออก สำหรับพื้นผิวที่มีรอย แตกกร้าว ให้อุดโป้ว ด้วยวัสดุอุดยาแนวที่เหมาะสม

สีรองพื้นที่เหมาะสม

พื้นผิวปูนใหม่

สีรองพื้นปูนกันต่างเจบีพีสมาร์ทโค้ท เบอร์ 8700 จำนวน 1 เที่ยว
กรณีงานเร่งด่วน หลังฉาบปูนทิ้งไว้ 2 วัน หรือกรณีพื้นผิวมีความชื้นรุนแรง (ความชื้นสูงถึง 25%) ให้ทาทับด้วยสีรองพื้นปูนใหม่และปูนเก่ากันชื้น เจบีพี สุพรีมโพรเมอร์ (สูตรน้ำ) เบอร์ 2900 จำนวน 1 เที่ยว

พื้นผิวปูนเก่า

ทาด้วยน้ำยาปรับสภาพพื้นผิวปูนเก่าที่เป็นฝุ่นซอล์ก JBP Chalky Wall Sealer (สูตรน้ำ) เบอร์ 900 หรือ เจบีพี มัลติเพอเพิสโพรเมอร์ (สูตรน้ำมัน) เบอร์ 2000 จำนวน 1 เที่ยว เพื่อเพิ่มประสิทธิภาพสูงสุดในการใช้งาน

การผสมน้ำและอัตราส่วน

การใช้งานสี

น้ำสะอาด โดยปริมาตร

ทา / กลิ้ง

ผสมน้ำโดยประมาณ 0 - 5 %

พ่น

ผสมน้ำโดยประมาณ 15 - 20%

การล้างทำความสะอาด

น้ำสะอาด

ข้อควรปฏิบัติและข้อควรระวัง

เก็บให้พ้นมือเด็ก เก็บในที่ที่มีอากาศถ่ายเทได้สะดวก ระวังเข้าตา ห้ามสูดดมและรับประทาน กวนสีให้เข้าเป็นเนื้อเดียวกันก่อนใช้งานปิดฝาให้สนิทเมื่อเลิกใช้งาน



Technical Data Sheet

JBP Smart Coat Semi-Gloss

DESCRIPTION	JBP Smart, with “Ultra Protection” technology, offers 2 times weather resistance qualification in order to protect your home to be durable in all weather conditions. JBP Smart also contains Microsphere Ceramic which can be a heat reflective insulation and reducing heat transfer into the building. Moreover, the arrangement of acrylic in forms of compact layer can help the qualification of washable, scrub resistance, excellent adhesion and durability. JBP Smart is safe to users and everyone. Suitable for stucco, concrete, brick, gypsum, asbestos and cement.																																										
SURFACE	Stucco, concrete, brick, gypsum board, asbestos cement sheet																																										
APPEARANCE	Semi-Gloss Finishes.																																										
COLOR	Shades as per catalogue.																																										
PHYSICAL PROPERTIES	<table border="0"> <tr> <td>TYPE OF VEHICLE</td> <td>:</td> <td>100% Acrylic Latex</td> </tr> <tr> <td>TYPE OF PIGMENT</td> <td>:</td> <td>Titanium dioxide and light fastness pigments</td> </tr> <tr> <td>TYPE OF SOLVENT</td> <td>:</td> <td>Water</td> </tr> <tr> <td>SOLID BY WEIGHT</td> <td>:</td> <td>33 - 35 % (Lab : Refer to White shade #G-200)</td> </tr> <tr> <td>SOLID BY VOLUME</td> <td>:</td> <td>23 - 25 % (Lab : Refer to White shade #G-200)</td> </tr> <tr> <td>RECOMMENDED DFT* PER COAT</td> <td>:</td> <td>35 - 40 micrometers</td> </tr> <tr> <td>WFT** TO YIELD RECOMMENDED DFT</td> <td>:</td> <td>150 - 160 micrometers</td> </tr> <tr> <td>THEORETICAL COVERAGE</td> <td>:</td> <td>32 - 37 sq.m. / gallon / coat</td> </tr> <tr> <td>PRACTICAL COVERAGE</td> <td>:</td> <td>27 - 31 sq.m. / gallon / coat</td> </tr> <tr> <td></td> <td></td> <td>(Reckoned with 15% Material loss) DRYING TIME 30°C</td> </tr> <tr> <td></td> <td></td> <td>*DFT = Dry film thickness, ** WFT=Wet film thickness</td> </tr> <tr> <td>TACK FREE</td> <td>:</td> <td>Within 30 minutes</td> </tr> <tr> <td>HARD DRY (RECOAT)</td> <td>:</td> <td>After 2 hours</td> </tr> <tr> <td>HANDLE</td> <td>:</td> <td>After 24 hours</td> </tr> </table>	TYPE OF VEHICLE	:	100% Acrylic Latex	TYPE OF PIGMENT	:	Titanium dioxide and light fastness pigments	TYPE OF SOLVENT	:	Water	SOLID BY WEIGHT	:	33 - 35 % (Lab : Refer to White shade #G-200)	SOLID BY VOLUME	:	23 - 25 % (Lab : Refer to White shade #G-200)	RECOMMENDED DFT* PER COAT	:	35 - 40 micrometers	WFT** TO YIELD RECOMMENDED DFT	:	150 - 160 micrometers	THEORETICAL COVERAGE	:	32 - 37 sq.m. / gallon / coat	PRACTICAL COVERAGE	:	27 - 31 sq.m. / gallon / coat			(Reckoned with 15% Material loss) DRYING TIME 30°C			*DFT = Dry film thickness, ** WFT=Wet film thickness	TACK FREE	:	Within 30 minutes	HARD DRY (RECOAT)	:	After 2 hours	HANDLE	:	After 24 hours
TYPE OF VEHICLE	:	100% Acrylic Latex																																									
TYPE OF PIGMENT	:	Titanium dioxide and light fastness pigments																																									
TYPE OF SOLVENT	:	Water																																									
SOLID BY WEIGHT	:	33 - 35 % (Lab : Refer to White shade #G-200)																																									
SOLID BY VOLUME	:	23 - 25 % (Lab : Refer to White shade #G-200)																																									
RECOMMENDED DFT* PER COAT	:	35 - 40 micrometers																																									
WFT** TO YIELD RECOMMENDED DFT	:	150 - 160 micrometers																																									
THEORETICAL COVERAGE	:	32 - 37 sq.m. / gallon / coat																																									
PRACTICAL COVERAGE	:	27 - 31 sq.m. / gallon / coat																																									
		(Reckoned with 15% Material loss) DRYING TIME 30°C																																									
		*DFT = Dry film thickness, ** WFT=Wet film thickness																																									
TACK FREE	:	Within 30 minutes																																									
HARD DRY (RECOAT)	:	After 2 hours																																									
HANDLE	:	After 24 hours																																									
STANDARD	TIS 2321-2549(Weather resistant emulsion paints)																																										
PACKAGING	<table border="0"> <tr> <td>Based Color</td> <td>:</td> <td>1 gallons (3.5 litres), 5 gallons (17.5 litres)</td> </tr> <tr> <td>Ready Mix</td> <td>:</td> <td>1 gallons (3.5 litres), 2.5 gallons (8.75 litres)</td> </tr> </table>	Based Color	:	1 gallons (3.5 litres), 5 gallons (17.5 litres)	Ready Mix	:	1 gallons (3.5 litres), 2.5 gallons (8.75 litres)																																				
Based Color	:	1 gallons (3.5 litres), 5 gallons (17.5 litres)																																									
Ready Mix	:	1 gallons (3.5 litres), 2.5 gallons (8.75 litres)																																									
SHELF LIFE	3 years at 30 - 35 °C																																										
CONDITIONS	Apply only when ambient temperature are between 13-38 °C and relative humidity <85%																																										



Technical Data Sheet

JBP Smart Coat Semi-Gloss

SURFACE PREPARATION

NEW SURFACE

Clean the surface until free from dust, cement, dirt and grease with clean cloth and water or detergent then leave the surface dry at least 1 month. Allow enough time for the surface to dry completely.

OLD SURFACE

Remove all deteriorated, loose, chalky old paint. Do not use wire brush due to it would cause corrosion. For fungi and algae infested area. it should be scrubbed with JBP MouldWash then leave it dry for 3 hours and no need to rinse off. Cracks on surface must be filled up with appropriate caulking compound

RECOMMENDED PRIMER

NEW SURFACE

JBP Smart Coat Alkali Resistant Primer for Exterior #8700 or immediately after stucco 2 day or humidity up to 45% with JBP Supreme Primer #2900 (Water Based)

OLD SURFACE

JBP Chalky Wall Sealer #900 (Water Based)

APPLICATION (MIXING RATIO)

Paint

Water by volume

BRUSH / ROLLER

0-5 %

SPRAY

15-20 %

CLEANING SOLVENT

Water

SAFETY PRECAUTIONS

Keep out of reach of children. Stored in a cool dry place with good ventilation. Avoid contact with eyes. Do not inhale vapor and swallow content. Stir thoroughly before and close container tightly after uses.